

Derbyshire County Council
Mike Ashworth, Strategic Director
Economy, Transport & Communities

Highways Laboratory
Ripley Road
Ambergate, Belper
Derbyshire, DE56 2ER

Steve Isaacs
Senior Project Engineer

Tel: 01629 532910
Email: steve.isaacs@derbyshire.gov.uk

CONTROLLED DOCUMENT (document is uncontrolled when printed)

Aggregates Approved for Asphalt Surfacing Materials & 14/20 PCC

PSV	Company	Quarry	Type	PSV	AAV	LA	W Abs
68	Aggregate Industries	Cwm Nant Lleici	Gritstone	68	11	26	1.7
	Aggregate Industries	Ghyll Scaur ¹	Andesitic Tuff	68	7	14	0.2
	Breedon Group	Barbae	Gritstone	68	8	17	1.4
	Breedon Group	Tan-y-Foel	Gritstone	68	10	16	0.8
	Cemex	Gilfach	Gritstone	68	8	20	1.1
	Hanson	Craig-yr-Hesg	Gritstone	68	9	23	0.6
	Tarmac	Bryn	Gritstone	68	8	28	1.4
	White Mountain	Ballystockart	Gritstone	68	8	12	1.3
65	Aggregate Industries	Haughmond Hill	Gritstone	65	4	14	0.7
	Breedon Group	Tongland	Gritstone	65	4	15	1.1
	Breedon Group	Tormitchel	Gritstone	65	10	18	1.8
	Cemex	Roan Edge	Gritstone	65	2	11	0.7
	Tarmac	Bayston Hill	Gritstone	65	4	14	1.4
	Tarmac	Dolyhir	Gritstone	65	5	14	0.5
	Tarmac	Gore	Gritstone	65	8	13	0.8
	White Mountain	Temple	Gritstone	65	6	10	0.7
60	Breedon Group	Leaton	Dolerite	60	5	19	1.0
	Breedon Group	Minffordd	Basalt	62	5	12	1.2
	Hanson	Builth Wells	Basalt	60	6	15	0.6
	Hanson	Criggion	Granite	60	6	16	0.9
	Hanson	Ingleton	Gritstone	60	4	12	0.6
	Harsco	Steelphalt	Steel Slag*	62#	10	15	2
	Tarmac	Mancetter	Basalt	60	6	10	1.6
	Tarmac	Santon	Steel Slag*	60#	2.8	12	1.7
< 60	Aggregate Industries	Bardon Hill	Andesite	57	3	14	0.4
	Aggregate Industries	Croft	Diorite	56	5	30	1.7
	Cemex	Middleton	Basalt	60	3	10	0.6
	MQP	Cliffe Hill	Diorite	55	2	13	0.5
	Tarmac	Mountsorrel	Granite	53	2	20	0.5

*Not to be used for coated chippings # PSV may not reflect final material performance

¹ Also known as Millom

Date of Issue: 11th January 2016

Updated 26th November 2018

Signed: S Isaacs

Senior Project Engineer